Low / Middle Alloy Type

Conformances


Applications

• Crane wheels, rod wheels, tractor roller

Features

- Submerged arc type hardfacing wire
- Low/Middle alloy type

Welding Position



Current

DC+

Welding Process

SAW(with S-717/S-401HF flux)

Diameter / Packaging

Diameter	Coil	Pac		
mm (in)	25kg (55lbs)	150kg (330lbs)	3	
3.2 (1/8)	\checkmark	√	√	

Typical Chemical Composition of All-Weld Metal (%)

	С	Si	Mn	Cr	Mo
As welded with 3.2mm wire	0.2	0.5	2.3	3.4	0.5

Typical Mechanical Properties of All-Weld Metal

	Rockwell Hardness(HRc) (≥3layers)	
On Mild Steel (3.2mm)	43~48	

Typical Welding Parameters

Diameter, Polarity Shielding Gas	CTWD mm (in)	Wire Feed Speed m/min (in/min)	Amp. (A)	Volt. (V)	Deposition Rate kg/hr (lb/hr)	
3.2mm (1/8in), DC+						
Submerged Arc	25 (1)	1.4 (58)	350	28	4.3 (9.4)	
		1.7 (70)	390	30	5.2 (11.4)	
		1.9 (76)	430	31	5.9 (12.9)	